

sikkens



Cetol[®] Door & Window



Simply Beautiful
WOOD CARE PRODUCTS

High Solids Alkyd

High Performance

Translucent, Gloss & Satin Finish



Cetol® Door & Window

Sikkens Cetol Door & Window is a high performance coating for specialty applications such as doors and windows. This alkyd high solids formulation offers optimum protection and a distinctive look for these unique areas. Available as a clear satin, clear gloss or 4 ready mix colors in satin. Cetol Door & Window offers a range of colors and sheens to enhance the beauty of any home. The high solids alkyd resin used in Cetol Door & Window is another example of the advancements central to the Sikkens “Next Wave” technology.



Exterior

Areas

- Doors
- Windows

Surfaces

- Garage Doors
- Fiberglass Doors



High Performance Film

The finish of Cetol Door & Window creates a protective film which gives a premium furniture look while still allowing all the natural character and grain of the wood to show through. The product creates a durable surface barrier to prevent weathering and is an excellent substitute for exterior varnishes and polyurethanes.

Tradition of Protection

Cetol Door & Window the “Next Wave” of technology is based on Sikkens industry leading experience in alkyd formulations creating durable and “Simply Beautiful” wood care products.




Satin Colors



006 Light Oak



009 Dark Oak



078 Natural



045 Mahogany

Clear Finishes



003 Clear Satin



003 Clear Gloss

Cetol Door & Window Technical Highlights

Feature	Technical Description	Benefits
High Solids Alkyd	Solids make up the film remaining on wood after coating dries	Fewer coats needed for optimum protection and premium look
Translucent Iron Oxide pigments and UV absorbers	Finely ground synthetic pigments and UV absorbing materials to protect against damaging UV rays	Combination gives high performance UV protection preventing graying and deterioration
Excellent Microporosity & Flexibility	Ability of coating to remain flexible and breathable	Prevents blistering and cracking due to expansion & contraction or moisture build up

Working With Cetol® Door & Window

■ Preparation Procedures

New, Weathered, Uncoated Wood

Sand door and window surfaces with 80-120 grit sandpaper prior to application of Cetol Door & Window.

The best method to prepare vertical wood surfaces is to sand with 80-120 grit sandpaper. However, an alternate to sanding for preparation is listed below.

Tips

- For best performance a total of 3 coats using any combination colors or clear topcoats should be applied
- For application on hardwoods immediately prior to applying coating wipe surface with acetone.
- It is always recommended to perform a three coat color test on a sample of the wood.
- Weathered wood affected with blue fungi or rust from nails may be treated after the surface preparation by applying a solution of 4 ounces of oxalic acid crystals in a gallon of warm water. This solution should be allowed to sit on the affected areas for 15-20 minutes before the final rinse with clean water. Let dry 3 days before coating.

■ Application Procedures

New/Bare Wood Applications

1. Follow the preparation procedures
2. Apply 1st coat of Cetol Door & Window
3. Let surface dry for minimum of 24 hours
4. Apply 2nd coat of Cetol Door & Window
5. Let surface dry for minimum of 24 hours
6. Apply 3rd coat of Cetol Door & Window
7. Clean tools with paint thinner or mineral spirits

Application Do's...

- Apply when the surface and air temp is 50°F/10°C to 95°F/35°C
- Saturate all end grains, nail holes and cracks in the wood
- Apply a medium coat using a soft long haired natural bristle brush
- Maintain a wet edge to prevent lap marks
- Fill joints, crack, nail holes with a good quality polyurathaneor acrylic caulk/filler prior to coating
- Apply in the direction of the wood grain
- Coat all sides of doors
- Stir well before using

Application Don'ts...

- Do not apply when the surface is hot to the touch
- Do not apply when dew or frost is present
- Do not apply over other coatings
- Do not apply in wet weather
- Do not apply when moisture content of the wood is greater than 18%
- Do not thin
- Do not use 3 coats of clear alone on areas which receive high levels of UV exposure

■ Maintenance Procedures

Proper maintenance starts with visual inspection. A timeframe of 2 to 3 years on the south & west exposure and 3 to 4 years on north & east exposures can be used as a general guideline. However, as weathering and exposure conditions can vary widely, maintenance may be needed sooner and should be performed when visually necessary regardless of timeframe.

Maintenance Preperation

1. Wet surface with clean water
2. Wash with 2 ounces of 100% powdered Tri-Sodium Phosphate (TSP) or phosphate-free substitute plus 1 quart of liquid bleach in 3 quarts of water.
3. Let the solution sit on the wood for 15-20 minutes. During this period, scrub the surface with a hard bristle brush. Do not let the solution dry on the wood or glass. Keep it wet.
4. Thoroughly rinse the cleaning solution from the wood with clean water.
5. Let dry 3 days before applying the coating.

Maintenance Applicaton

1. Apply one coat of Cetol Door & Window



Cetol® Door & Window

This "Next Wave" product is the next generation of translucent coatings from Sikkens.

Sikkens "Simply Beautiful" wood care products are known throughout the industry as offering unrivaled looks, durability and performance for all types of wood. Cetol Door & Window has been specially formulated to maximize the longevity and beauty of exterior wood doors and windows.



Simply Beautiful™